

Elastocon® 2810

TPE

Elastocon TPE Technologies

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	1.57	MPa	ASTM D 638
Modulus at 100% Elongation	0.496	MPa	ASTM D 412
Shore A Hardness	10	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	860	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion, Blow Molding

Certifications

Food contact, Food approval FDA 21 CFR

Delivery form

Pellets

Applications

Medical

Features

Soft Feel

Regional Availability

North America