

| Mechanical properties | Value | Unit | Test Standard |
|----------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength | 5.67 | MPa | ASTM D 638 |
| Modulus at 100% Elongation | 1.98 | MPa | ASTM D 412 |
| Shore A Hardness | 58 | - | ASTM D 2240 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 1030 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Injection Molding, Other Extrusion, Blow Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Features

Tribologic Grade

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Medical

Regional Availability

North America