

Elastocon® 8068B

TPE

Elastocon TPE Technologies

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	7.85	MPa	ASTM D 638
Modulus at 100% Elongation	2.8	MPa	ASTM D 412
Shore A Hardness	73	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion, Blow Molding

Applications

Medical

Delivery form

Pellets, Black

Regional Availability

North America

Special Characteristics

U.V. stabilized or stable to weather