

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	7.85	MPa	ASTM D 638
Modulus at 100% Elongation	4.1	MPa	ASTM D 412
Shore A Hardness	72	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Other Extrusion, Blow Molding

Delivery form

Pellets

Additives

Lubricants

Special Characteristics

U.V. stabilized or stable to weather

Features

Tribologic Grade

Applications

Medical

Regional Availability

North America