

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength	7.85	MPa	ASTM D 638
Modulus at 100% Elongation	2.79	MPa	ASTM D 412
Shore A Hardness	73	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	1030	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding, Other Extrusion, Blow Molding

### Delivery form

Pellets

### Special Characteristics

U.V. stabilized or stable to weather

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Medical

### Regional Availability

North America