

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	9.97	MPa	ASTM D 638
Modulus at 100% Elongation	7.11	MPa	ASTM D 412
Shore A Hardness	88	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	990	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding, Other Extrusion, Blow Molding

Delivery form

Pellets

Special Characteristics

U.V. stabilized or stable to weather

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Medical

Regional Availability

North America