

**Enduraprene™ E3390A-1i8.6**

TPE

GDC Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>8.6</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>7.5</b>	MPa	ASTM D 638
Elongation at Break	<b>155</b>	%	ASTM D 638
Shore A Hardness	<b>90</b>	-	ASTM D 2240

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>970</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Certifications**

Recycled Resin Content

**Applications**

Automotive

**Regional Availability**

North America, South and Central America