

Evoprene® 003

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	5.5	MPa	ISO 37
Strain at break	665	%	ISO 37
Tear strength	28	kN/m	ISO 34-1
Abrasion resistance	325	mm ³	ISO 4649
Shore A hardness	40	-	ISO 7619-1
Other Standards^{S1}			
Stress at 100% elongation	1.5	MPa	ISO 37
Stress at 300% elongation	8.7	MPa	ISO 37

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^{S1}			
Density	990	kg/m ³	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe