

**Evoprene® 022**

TPE

Alphagary

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>6.1</b>	MPa	ISO 37
Strain at break	<b>655</b>	%	ISO 37
Tear strength	<b>32</b>	kN/m	ISO 34-1
Abrasion resistance	<b>240</b>	mm <sup>3</sup>	ISO 4649
Shore A hardness	<b>54</b>	-	ISO 7619-1
<b>Other Standards<sup>S1</sup></b>			
Stress at 100% elongation	<b>1.9</b>	MPa	ISO 37
Stress at 300% elongation	<b>9.6</b>	MPa	ISO 37

S: These properties are reported by the producer according standards that are different to our defaults.

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>Other Standards<sup>S1</sup></b>			
Density	<b>990</b>	kg/m <sup>3</sup>	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe