

Evoprene® 072

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	4.8	MPa	ISO 37
Strain at break	700	%	ISO 37
Shore A hardness	50	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Other Standards^[S]			
Density	1100	kg/m ³	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe