

Evoprene® 689

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	4.5	MPa	ISO 37
Strain at break	840	%	ISO 37
Shore A hardness	46	-	ISO 7619-1
Other Standards^[S]			
Stress at 100% elongation	0.8	MPa	ISO 37
Stress at 300% elongation	3.9	MPa	ISO 37
Tear strength	17	kN/m	ISO 6383
Abrasion resistance	399	mm ³	DIN 53516

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	980	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe