

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	2.7	MPa	ISO 37
Strain at break	460	%	ISO 37
Compression set at 70 °C, 24h	68	%	ISO 815
Compression set at 100 °C, 24h	82	%	ISO 815
Shore A hardness	40	-	ISO 7619-1
<b>Other Standards<sup>[S]</sup></b>			
Stress at 100% elongation	1.4	MPa	ISO 37
Stress at 300% elongation	8.4	MPa	ISO 37
Tear strength	21	kN/m	ISO 6383

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
<b>Other Standards<sup>[S]</sup></b>			
Density	950	kg/m <sup>3</sup>	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe