

Evoprene® COGEE 5846

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	5.5	MPa	ISO 37
Strain at break	572	%	ISO 37
Compression set at 70 °C, 24h	75	%	ISO 815
Shore A hardness	66	-	ISO 7619-1
Other Standards^[S]			
Stress at 100% elongation	2.6	MPa	ISO 37
Stress at 300% elongation	10.8	MPa	ISO 37
Tear strength	35	kN/m	ISO 6383
Abrasion resistance	191	mm ³	DIN 53516

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^[S]			
Density	1200	kg/m ³	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe