

# Evoprene® G 251-40 NATURAL

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Modulus at 300% Elongation	1.38	MPa	ASTM D 412
Shore A Hardness	40	-	ASTM D 2240
Tear Strength	19.3	kN/m	ASTM D 624
Tensile Strength	4.14	MPa	ASTM D 412
Elongation at Break	400	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding, Other Extrusion

### Regional Availability

North America, Europe

### Delivery form

Natural Color