

Evoprene® G 925

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	5.5	MPa	ISO 37
Strain at break	600	%	ISO 37
Compression set at 70 °C, 24h	59	%	ISO 815
Compression set at 100 °C, 24h	77	%	ISO 815
Shore A hardness	34	-	ISO 7619-1
Other Standards^{S1}			
Stress at 100% elongation	0.9	MPa	ISO 37
Stress at 300% elongation	5.4	MPa	ISO 37

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Other Standards^{S1}			
Density	890	kg/m ³	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe