

# Evoprene® Super G 948

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	7.4	MPa	ISO 37
Strain at break	510	%	ISO 37
Compression set at 70 °C, 24h	18	%	ISO 815
Tear strength	20	kN/m	ISO 34-1
Shore A hardness	47	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
<b>Other Standards<sup>[5]</sup></b>			
Density	1080	kg/m <sup>3</sup>	ISO 2781

S: These properties are reported by the producer according standards that are different to our defaults.

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe