

Evoprene® TS 7091B-800 BLACK

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 300% Elongation	2.24	MPa	ASTM D 412
Shore A Hardness	42	-	ASTM D 2240
Tear Strength	14.9	kN/m	ASTM D 624
Tensile Strength	3.45	MPa	ASTM D 412
Elongation at Break	500	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1150	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

North America, Europe

Delivery form

Black