

**Evoprene® TS 7103 (68) NATURAL 4179**

TPE

Alphagary

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>10</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>5</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Shore A Hardness	<b>74</b>	-	ASTM D 2240
Compression Set , 22 hr @ 158 °F	<b>56</b>	%	ASTM D 395
Tensile Strength	<b>11</b>	MPa	ASTM D 412
Elongation at Break	<b>650</b>	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	<b>980</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe

**Delivery form**

Natural Color