

Evoprene® TS 7118 D-M1 (35) UV 0200 BL

TPE

Alphagary

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.6	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	39	-	ASTM D 2240
Tensile Strength	8.96	MPa	ASTM D 412
Elongation at Break	700	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	960	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding, Profile Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Delivery form

Black

Regional Availability

North America, Europe