

## Faraprene C100-75A black

TPE

Primex Color, Compounding & Additives

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	20	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Modulus at 100% Elongation	3.34	MPa	ASTM D 412
Shore A Hardness	75	-	ASTM D 2240
Tear Strength	48.1	kN/m	ASTM D 624
Tensile Strength at Break	15.5	MPa	ASTM D 412
Elongation at Break	1000	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding, Other Extrusion

#### Features

Scratch Resistant

#### Delivery form

Black

#### Regional Availability

North America