

Faraprene H300-95A

TPE

Primex Color, Compounding & Additives

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	30.1	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	7.11	MPa	ASTM D 412
Shore A Hardness	96	-	ASTM D 2240
Tear Strength	49	kN/m	ASTM D 624
Tensile Strength at Break	10.4	MPa	ASTM D 412
Elongation at Break	416	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1170	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Good Adhesion

Applications

Automotive, General Purpose, Sports Equipment

Regional Availability

North America