

GFE 4762-A5 NAT LCF

TPE

Alphagary

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	74	-	ASTM D 2240
Tensile Strength	13.8	MPa	ASTM D 412
Elongation at Break	340	%	ASTM D 412

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Limiting Oxygen Index	23	%	ASTM D 2863

Other properties	Value	Unit	Test Standard
Density	1160	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Natural Color

Regional Availability

North America, Europe