

**GFG 7795-A7 NAT**

TPE

Alphagary

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Shore D Hardness	<b>48</b>	-	ASTM D 2240
Tear Strength	<b>65.6</b>	kN/m	ASTM D 624
Tensile Strength	<b>17.2</b>	MPa	ASTM D 412
Elongation at Break	<b>550</b>	%	ASTM D 412

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1190</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Natural Color

**Applications**

Automotive

**Special Characteristics**

Flame retardant

**Regional Availability**

North America, Europe