

**Product Texts**

Available in natural and light-grey color.

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	40	g/10min	ISO 1133
Temperature	190	°C	-
Load	5	kg	-

**Mechanical properties**

**ISO Data**

	Value	Unit	Test Standard
Strain at break	630	%	ISO 527
Shore A hardness	70	-	ISO 7619-1

**Other properties**

	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ISO 1183

**Processing Recommendation Injection Molding**

	Value	Unit	Test Standard
Melt temperature	180	°C	-
Mold temperature	30	°C	-

**Characteristics**

**Processing**

Injection Molding

**Chemical Resistance**

Solvent Resistance, Ozone Resistance

**Special Characteristics**

Light stabilized or stable to light, Heat stabilized or stable to heat

**Regional Availability**

Europe

**Features**

Copolymer