

Product Texts

P5200 is a HDPE pipe grade produced by Mitsui CX Process.

P5200 combines excellent processability with good creep resistance, ESCR and mechanical properties.

P5200UV is stabilized adequately with HALS+ to give a long service life under outdoor exposure & recommended for telecom ducts.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.2	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	25	MPa	ASTM D 638
Tensile Strength at Break	38	MPa	ASTM D 638
Elongation at Yield	7	%	ASTM D 638
Elongation at Break	850	%	ASTM D 638
Flexural Modulus	1000	MPa	ASTM D 790
Shore D Hardness	65	-	ASTM D 2240
Izod Impact notched, 1/8 in	175	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	64	°C	ASTM D 648
Melting Temperature	131	°C	ASTM D 3418
Vicat Temperature	125	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	950	kg/m ³	ASTM D 792

Processing Recommendation Extrusion	Value	Unit	Test Standard
Zone 1	150 - 180	°C	-
Nozzle temperature	170 - 180	°C	-

Characteristics

Processing

Pipe/Tube Extrusion

Special Characteristics

U.V. stabilized or stable to weather

Features

Creep Resistance

Chemical Resistance

Environmental Stress Crack Resistance

Applications

Electrical and Electronical

Regional Availability

Asia Pacific