

POLYelast TPE Z805P

TPE

Polykemi AB

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.7	%	ISO 294-4, 2577
Molding shrinkage, normal	1.7	%	ISO 294-4, 2577
Mechanical properties			
ASTM Data			
Shore A Hardness	80	-	ASTM D 2240
Other properties			
Density	1080	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Granules

Special Characteristics

U.V. stabilized or stable to weather

Chemical Resistance

Ozone Resistance

Regional Availability

Europe, Asia Pacific