

Prime Co Faraprene 200

TPE

Primex Color, Compounding & Additives

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.049	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	8.96	MPa	ASTM D 412
Shore A Hardness	90	-	ASTM D 2240
Shore D Hardness	45	-	ASTM D 2240
Tensile Strength at Break	11	MPa	ASTM D 412
Elongation at Break	843	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	968	kg/m ³	ASTM D 792

Characteristics

Features

Good Adhesion, Low Odor

Regional Availability

North America

Applications

Automotive, Packaging