

RESIPRENE® 1065

TPE

Resirene

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Shore A hardness	65	-	ISO 7619-1
ASTM Data			
Tensile Strength at Break	3.24	MPa	ASTM D 638
Elongation at Break	1260	%	ASTM D 638
Other properties			
Density	1100	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Features

Soft Feel