

RESIPRENE® 1085

TPE

Resirene

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	200	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Shore A hardness	85	-	ISO 7619-1
ASTM Data			
Tensile Strength at Break	3.86	MPa	ASTM D 638
Elongation at Break	175	%	ASTM D 638
Other properties			
Density	1000	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Features

Soft Feel