

RTP 6042-40A MD NATURAL

TPE

RTP Company

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 100% Elongation	1.17	MPa	ASTM D 412
Shore A Hardness	40	-	ASTM D 2240
Tear Strength	22.8	kN/m	ASTM D 624
Compression Set , 22 hr @ 73 °F	20	%	ASTM D 395
Compression Set , 22 hr @ 158 °F	75	%	ASTM D 395

Other properties	Value	Unit	Test Standard
Density	1090	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	82.2	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	193 - 238	°C	-
Mold temperature	21.1 - 48.9	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

Natural Color