

Product Texts

Hydrogenated styrene farnesene block copolymer (HSFC)

Styrene content: 21%

SEPTON™ BIO-series enables new solutions with high bio-based content to meet the emerging demand for more sustainable materials. Main applications are TPE compounds, adhesives, consumer goods, mobility and sport goods & footwear.

Processing/Physical Characteristics	Value	Unit	Test Standard
Other Standards^[5]			
Melt flow index, MFI	48	g/10min	
Temperature	230	°C	-
Load	2.16	kg	-

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
Other Standards^[5]			
Shore A hardness	25	-	

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Delivery form

Pellets

Applications

Sports Equipment

Features

Good Adhesion, Copolymer

Regional Availability

North America, Europe, Asia Pacific

Certifications

Contains renewable resources