

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	31	g/10min	ISO 1133
Temperature	190	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	8.7	MPa	ISO 37
Strain at break	640	%	ISO 37
Compression set at 23 °C, 24h	37	%	ISO 815
Compression set at 70 °C, 24h	57	%	ISO 815
Compression set at 100 °C, 24h	75	%	ISO 815
Tear strength	29	kN/m	ISO 34-1
ASTM Data			
Shore A Hardness	80	-	ASTM D 2240
Other Standards^[5]			
Stress at 100% elongation	4	MPa	DIN 53504
Stress at 300% elongation	4.9	MPa	DIN 53504

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1020	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

Opaque

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa