

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	19	g/10min	ISO 1133
Temperature	190	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Strength	4.3	MPa	ISO 37
Strain at break	660	%	ISO 37
Compression set at 23 °C, 24h	21	%	ISO 815
Compression set at 70 °C, 24h	41	%	ISO 815
Compression set at 100 °C, 24h	63	%	ISO 815
Tear strength	16	kN/m	ISO 34-1
<b>ASTM Data</b>			
Shore A Hardness	55	-	ASTM D 2240
<b>Other Standards<sup>[5]</sup></b>			
Stress at 100% elongation	1.6	MPa	DIN 53504
Stress at 300% elongation	2.2	MPa	DIN 53504

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	1180	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Injection Molding

### Special Characteristics

Opaque

### Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa