

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	3.1	MPa	ASTM D 638
Elongation at Yield	650	%	ASTM D 638
Flexural Modulus	34.47	MPa	ASTM D 790
Shore A Hardness	60	-	ASTM D 2240
Izod Impact notched, 1/8 in	N	J/m	ASTM D 256
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Regional Availability

North America