

StarBond™ 58800

TPE

Star Thermoplastics

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Modulus at 300% Elongation	3.56	MPa	ASTM D 412
Shore A Hardness	60	-	ASTM D 2240
Tear Strength	35.7	kN/m	ASTM D 624
Tensile Strength	3.59	MPa	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Black

Features

Good Adhesion, Soft Feel

Special Characteristics

U.V. stabilized or stable to weather

Regional Availability

North America