

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Modulus at 300% Elongation	4.19	MPa	ASTM D 412
Shore A Hardness	69	-	ASTM D 2240
Tear Strength	44.6	kN/m	ASTM D 624
Tensile Strength	9.56	MPa	ASTM D 412
Elongation at Break	739	%	ASTM D 412

Other properties	Value	Unit	Test Standard
Density	890	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Processing

Injection Molding, Other Extrusion

#### Special Characteristics

Translucent

#### Certifications

Food contact, Food approval FDA 21 CFR, RoHS compliant

#### Applications

Medical

#### Regional Availability

North America