

Tefabloc™ SE6300C

TPE

Mitsubishi Chemical Performance Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	150	g/10min	ISO 1133
Temperature	230	°C	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Shore A hardness	60	-	ISO 7619-1
Other Standards^[5]			
Stress at break TPE	3	MPa	ISO 37
Strain at break TPE	440	%	ISO 37

S: These properties are reported by the producer according standards that are different to our defaults.

Other properties	Value	Unit	Test Standard
Density	890	kg/m ³	ISO 1183

Characteristics**Processing**

Additive Manufacturing

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Translucent