

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	14.7	MPa	ISO 37
Strain at break	787	%	ISO 37
Tear strength	25.5	kN/m	ISO 34-1
Shore A hardness	73	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	915	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	200 - 250	°C	-
Mold temperature	25 - 40	°C	-
Zone 1	180	°C	-
Zone 2	200	°C	-
Zone 3	220	°C	-
Injection pressure	20 - 100	MPa	-
Back pressure	2 - 10	MPa	-
Holding pressure	8 - 60	MPa	-

Characteristics

Processing
Injection Molding

Applications
Automotive

Special Characteristics
U.V. stabilized or stable to weather

Regional Availability
North America, Europe, Asia Pacific

Features
Good Adhesion