

THERMOLAST® K TC6FLZ

TPE

KRAIBURG TPE GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	2.9	MPa	ISO 37
Strain at break	600	%	ISO 37
Compression set at 70 °C, 24h	63	%	ISO 815
Compression set at 100 °C, 24h	93	%	ISO 815
Tear strength	14	kN/m	ISO 34-1
Shore A hardness	58	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Melt temperature	180 - 220	°C	-
Mold temperature	25 - 40	°C	-
Injection pressure	20 - 100	MPa	-
Back pressure	2 - 10	MPa	-
Holding pressure	8 - 60	MPa	-
Maximum residence time	10	min	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Black

Special Characteristics

Flame retardant, Halogen-free

Features

Good Adhesion

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific