

THERMOLAST® K TF3BTL

TPE

KRAIBURG TPE GmbH & Co. KG

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Tensile Strength | 6.2 | MPa | ISO 37 |
| Strain at break | 850 | % | ISO 37 |
| Tear strength | 7.4 | kN/m | ISO 34-1 |
| Shore A hardness | 28 | - | ISO 7619-1 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 880 | kg/m ³ | ISO 1183 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|-----------------|-------------|----------------------|
| Pre-drying - Temperature | 60 - 80 | °C | - |
| Pre-drying - Time | 2 - 4 | h | - |
| Injection pressure | 20 - 100 | MPa | - |
| Back pressure | 2 - 10 | MPa | - |
| Holding pressure | 8 - 60 | MPa | - |
| Maximum residence time | 10 | min | - |

Characteristics**Processing**

Injection Molding

Special Characteristics

Translucent

Features

Good Adhesion

Certifications

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific