

THERMOLAST® K TL60WG-BLCK

TPE

KRAIBURG TPE GmbH & Co. KG

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	2.7	MPa	ISO 37
Strain at break	250	%	ISO 37
Compression set at 70 °C, 24h	24	%	ISO 815
Tear strength	10.5	kN/m	ISO 34-1
Shore A hardness	60	-	ISO 7619-1

Other properties	Value	Unit	Test Standard
Density	725	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Delivery form

Black

Special Characteristics

U.V. stabilized or stable to weather

Features

Good Adhesion, Soft Feel

Applications

Automotive, Encapsulation

Regional Availability

North America, Europe, Asia Pacific