

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>8.1</b>	MPa	ISO 37
Strain at break	<b>580</b>	%	ISO 37
Tear strength	<b>15.3</b>	kN/m	ISO 34-1
Shore A hardness	<b>58</b>	-	ISO 7619-1
<b>Other properties</b>			
Density	<b>990</b>	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>2 - 6</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>180 - 220</b>	°C	-
Mold temperature	<b>40 - 60</b>	°C	-
Zone 1	<b>180 - 190</b>	°C	-
Zone 2	<b>190 - 200</b>	°C	-
Zone 3	<b>200 - 220</b>	°C	-
Injection pressure	<b>20 - 100</b>	MPa	-
Back pressure	<b>2 - 10</b>	MPa	-
Holding pressure	<b>8 - 60</b>	MPa	-
Maximum residence time	<b>10</b>	min	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Natural Color

**Special Characteristics**

Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization

**Features**

Good Adhesion, Soft Feel

**Chemical Resistance**

Radiation Resistance

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR, Medical Grade, Biocompatibility ISO 10993, RoHS compliant, REACH

**Applications**

Medical

**Regional Availability**

North America, Europe, Asia Pacific