

Product Texts

Recycled raw materials content: 22 %

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Strength	6	MPa	ISO 37
Strain at break	600	%	ISO 37
Tear strength	15	kN/m	ISO 34-1
Shore A hardness	62	-	ISO 7619-1

Other properties

	Value	Unit	Test Standard
Density	885	kg/m ³	ISO 1183

Processing Recommendation Injection Molding

	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	200 - 250	°C	-
Mold temperature	25 - 40	°C	-
Zone 1	180	°C	-
Zone 2	200	°C	-
Zone 3	220	°C	-
Injection pressure	20 - 100	MPa	-
Back pressure	2 - 10	MPa	-
Holding pressure	8 - 60	MPa	-
Maximum residence time	10	min	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Features

Good Adhesion

Certifications

Recycled Resin Content

Regional Availability

North America, Europe, Asia Pacific