

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	160	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Stress at 100% elongation	0.4	MPa	ISO 527
Strain at break TPE	>300	%	ISO 527
Compression set at 23 °C, 24h	17	%	ISO 815
ASTM Data			
Shore A Hardness	20	-	ASTM D 2240
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	91	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-65	°C	ISO 11357-1/-2
Other properties			
Density	900	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Mold temperature	20 - 60	°C	-
Feed temperature	20 - 30	°C	-
Zone 1	140 - 200	°C	-
Nozzle temperature	170 - 210	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Translucent, Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization

Chemical Resistance

Oxidation Resistance, Radiation Resistance

Certifications

Medical Grade, Biocompatibility ISO 10993

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa