

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Stress at 100% elongation	2.4	MPa	ISO 527
Strain at break TPE	>300	%	ISO 527
Compression set at 23 °C, 24h	30	%	ISO 815
Compression set at 70 °C, 24h	46	%	ISO 815
Compression set at 100 °C, 24h	51	%	ISO 815
ASTM Data			
Shore A Hardness	60	-	ASTM D 2240
Shore D Hardness	14	-	ASTM D 2240
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	152	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-63	°C	ISO 11357-1/-2
Other properties			
Density	880	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Mold temperature	20 - 60	°C	-
Feed temperature	20 - 30	°C	-
Zone 1	140 - 210	°C	-
Nozzle temperature	180 - 220	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Translucent, Sterilizable, Ethylene Oxide (EtO) Sterilization, Steam sterilization, Gamma irradiation sterilization

Chemical Resistance

Oxidation Resistance, Radiation Resistance

Certifications

Medical Grade, Biocompatibility ISO 10993

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa