

Tefabloc™ TO CA 190

TPE

Mitsubishi Chemical Performance Polymers

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Shore A hardness	85	-	ISO 7619-1
Shore D hardness	61	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Oxygen index	25	%	ISO 4589-1/-2

Characteristics**Processing**

Wire/Cable Extrusion

Applications

Automotive, Electrical and Electronical

Special Characteristics

Flame retardant

Regional Availability

North America, Europe, Asia Pacific