

**Tefabloc™ TO CA 809**

TPE

Mitsubishi Chemical Performance Polymers

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Shore A hardness	<b>75</b>	-	ISO 7619-1
Shore D hardness	<b>41</b>	-	ISO 7619-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Oxygen index	<b>25</b>	%	ISO 4589-1/-2

**Characteristics****Processing**

Wire/Cable Extrusion

**Applications**

Automotive, Electrical and Electronical

**Special Characteristics**

Flame retardant

**Regional Availability**

North America, Europe, Asia Pacific