

**Tefabloc™ TO SI 036**

TPE

Mitsubishi Chemical Performance Polymers

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Shore A hardness	<b>80</b>	-	ISO 7619-1

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Oxygen index	<b>28</b>	%	ISO 4589-1/-2

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific

**Special Characteristics**

Flame retardant