

**Unipren® A3 20A XP01 CRLA010 UP347**

Grupo Petropol Polímeros

TPE

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Shore A Hardness	<b>20</b>	-	ASTM D 2240

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>890</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>60 - 80</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Melt temperature	<b>180 - 200</b>	°C	-
Mold temperature	<b>40</b>	°C	-

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Features**

Good Adhesion

**Special Characteristics**

Transparent

**Regional Availability**

North America, Europe, South and Central America