

Unipren® A3 CRLA010 40A UP373

TPE

Grupo Petropol Polímeros

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Shore A Hardness	40	-	ASTM D 2240

Other properties	Value	Unit	Test Standard
Density	880	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	60 - 80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	180 - 220	°C	-
Mold temperature	40	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Features

Good Adhesion

Delivery form

Natural Color

Regional Availability

North America, Europe, South and Central America